






















ASATHIO COLOURS (1)		Dyeing depth (% owf)	Fastness					
Dyeing Colour Sample	Product Name		Light	Washing			Rubbing	
				Shade Change	Staining		DRY	WET
					on Cotton	on Rayon		
	Yellow GG(F)	3	4	4	4	4-5	4	2-3
	Orange OA(F)	3	4	4-5	4-5	5	3	2
	Brown 3RN	6	3-4	3-4	4-5	5	3	2-3
	Brill. Red BB	6	4-5	4	4-5	4-5	2-3	2
	Red Brown 3B	6	3-4	3-4	4	4-5	2-3	2-3
	Red Brown 6R conc	6	4-5	4-5	4-5	4-5	3-4	2-3
	Brown SR	6	2-3	3-4	5	5	3-4	2-3
	Dark Brown D 200%	6	5	4-5	4-5	5	4	2-3
	Brown GRN	6	5	4-5	4-5	5	4	2-3
	Black Brown GN	6	6	4-5	5	5	3-4	2-3
	Olive BKN 200%	3	3	4-5	4-5	4-5	4	2

Fastness Light : AATCC 16.3 (Xenon lamp)

ASATHIO COLOURS (2)		Dyeing depth (% owf)	Fastness					
Dyeing Colour Sample	Product Name		Light	Washing			Rubbing	
				Shade Change	Staining		DRY	WET
					on Cotton	on Rayon		
	Olive BBK 200	3	4	4	4-5	5	4	2
	Brill. Green 5GFF	3	4-5	4	4-5	4-5	4	4
	Dark Green 3GF	3	5	4	4-5	4-5	4	3
	Light Green BG	3	4-5	4	4-5	4-5	4-5	2-3
	Pure Blue 6G	3	5	4	4	4-5	4-5	3
	Pure Blue 3GL	3	5	4	4	4-5	2-3	2
	Pure Blue 2R	3	5-6	4	4	4-5	4-5	3
	Navy Blue 2B	6	6	4	5	5	4	2
	Blue 3B143	3	4-5	3-4	4	4-5	4-5	2
	Black 3RCN	4.5	6	4-5	5	5	2	1
	Black L-RCN (Liquid Type)	12	6	4-5	5	5	2	1

Washing : AATCC 61 (II A 49°C)

Rubbing : AATCC 8